



AdmireCera Corporation

Quality specification of Kraft Board Grade Paper (Ply Bond 350/450 J/m²)

Substance	Ply-Bond	B.F.	RCT (Kn/M)	Cobb	Moisture	Caliper	Bulk
GSM	J/m ²	***	MD/CD	G/m ²	%	Mm	Cc/g
180	350	16	2.21/1.64	100-150	6	0.25-0.28	1.47
220	350	16	2.80/2.00	100-150	6	0.31-0.34	1.47
250	350	15	3.30/2.30	100-150	6	0.34-0.38	1.44
300	350	13-14	4.50/3.40	100-150	6	0.42-0.44	1.43
325	350	13-14	4.70/3.60	100-150	6	0.46-0.48	1.44
350	350	12-13	5.50/4.10	100-150	6	0.49-0.53	1.46
400	400	11-12	6.00/4.50	150+	6	0.56-0.59	1.44
450	450	11-12	6.30/4.80	150+	6	0.63-0.66	1.43
350	450	12-13	6.10/4.50	150+	6	0.47-0.50	1.38
450	450	12-13	6.80/5.50	150+	6	0.60-0.62	1.35
350	500	16-17	6.50/5.10	150+	6	0.47-0.50	1.38
350	600	17-18	7.00/5.30	150+	6	0.46-0.50	1.37
350	700	18-19	7.50/6.00	150+	6	0.45-0.49	1.34
350	800	19-20	8.00/6.20	150+	6	0.45-0.49	1.34

Base for POY, Text Tube / Paper Cones / Core Pipe / Chemical Drug Containers.

Tolerance :-

GSM ±5%

Moisture ±1%

Plybond- 350 to 600 ±10

700 to 800 (-)20/30