



18 BF PARAMETER

Property	Unit	Method	AdmireCera Corporation									
			90	100	120	140	150	170	180	200	220	250
Grammage	g/m ²	ISO 536	90	100	120	140	150	170	180	200	220	250
Grammage avg.	± 5 %		95-100	95-105	114-126	133-147	143-157	162-178	172-189	190-200	209-231	238-262
Moisture	%	ONLINE	6.5-7.0	6.5-7.0	7.0-7.5	7.0-7.5	7.0-7.5	7.5-8.0	7.5-8.0	8.0-8.5	8.0-8.5	8.0-8.5
Cobb (60sec)	g/m ²	ISO 535	35-40	35-40	40-45	40-45	40-45	40-45	40-45	45-50	45-50	45-50
Bulk	cc/g	ISO 534	1.50-1.60	1.50-1.60	1.45-1.55	1.40-1.45	1.40-1.45	1.40-1.45	1.37-1.45	1.37-1.45	1.37-1.45	1.37-1.45
RCT CD	kn/m	ISO 12192	0.55	0.65	0.75	1.00	1.10	1.25	1.45	1.65	1.75	1.90
Bursting Strength	kg/cm ²	ISO 2758	1.62	1.80	2.16	2.52	2.70	3.06	3.24	3.60	3.96	4.50

20 BF PARAMETER

Property	Unit	Method	AdmireCera Corporation									
			90	100	120	140	150	170	180	200	220	250
Grammage	g/m ²	ISO 536	90	100	120	140	150	170	180	200	220	250
Grammage avg.	± 5 %		95-100	95-105	114-126	133-147	143-157	162-178	172-189	190-200	209-231	238-262
Moisture	%	ONLINE	6.5-7.0	6.5-7.0	7.0-7.5	7.0-7.5	7.0-7.5	7.5-8.0	7.5-8.0	8.0-8.5	8.0-8.5	8.0-8.5
Cobb (60sec)	g/m ²	ISO 535	35-40	35-40	40-45	40-45	40-45	40-45	40-45	45-50	45-50	45-50
Bulk	cc/g	ISO 534	1.50-1.60	1.50-1.60	1.45-1.55	1.40-1.45	1.40-1.45	1.40-1.45	1.37-1.45	1.37-1.45	1.37-1.45	1.37-1.45
RCT CD	kn/m	ISO 12192	0.65	0.70	0.85	1.15	1.20	1.30	1.55	1.75	1.85	2.15
Bursting Strength	kg/cm ²	ISO 2758	1.80	2.00	2.40	2.80	3.00	3.40	3.60	4.00	4.40	5.00

22 BF PARAMETER

Property	Unit	Method	AdmireCera Corporation									
			90	100	120	140	150	170	180	200	220	250
Grammage	g/m ²	ISO 536	90	100	120	140	150	170	180	200	220	250
Grammage avg.	± 5 %		95-100	95-105	114-126	133-147	143-157	162-178	172-189	190-200	209-231	238-262
Moisture	%	ONLINE	6.5-7.0	6.5-7.0	7.0-7.5	7.0-7.5	7.0-7.5	7.5-8.0	7.5-8.0	8.0-8.5	8.0-8.5	8.0-8.5
Cobb (60sec)	g/m ²	ISO 535	35-40	35-40	40-45	40-45	40-45	40-45	40-45	45-50	45-50	45-50
Bulk	cc/g	ISO 534	1.50-1.60	1.50-1.60	1.45-1.55	1.40-1.45	1.40-1.45	1.40-1.45	1.37-1.45	1.37-1.45	1.37-1.45	1.37-1.45
RCT CD	kn/m	ISO 12192	0.75	0.80	1.00	1.28	1.35	1.45	1.65	1.90	1.95	2.28
Bursting Strength	kg/cm ²	ISO 2758	1.98	2.20	2.64	3.08	3.30	3.74	3.96	4.40	4.84	5.50

24 BF PARAMETER

Property	Unit	Method	AdmireCera Corporation									
			90	100	120	140	150	170	180	200	220	250
Grammage	g/m ²	ISO 536	90	100	120	140	150	170	180	200	220	250
Grammage avg.	± 5 %		95-100	95-105	114-126	133-147	143-157	162-178	172-189	190-200	209-231	238-262
Moisture	%	ONLINE	6.5-7.0	6.5-7.0	7.0-7.5	7.0-7.5	7.0-7.5	7.5-8.0	7.5-8.0	8.0-8.5	8.0-8.5	8.0-8.5
Cobb (60sec)	g/m ²	ISO 535	35-40	35-40	40-45	40-45	40-45	40-45	40-45	45-50	45-50	45-50
Bulk	cc/g	ISO 534	1.50-1.60	1.50-1.60	1.45-1.55	1.40-1.45	1.40-1.45	1.40-1.45	1.37-1.45	1.37-1.45	1.37-1.45	1.37-1.45
RCT CD	kn/m	ISO 12192	0.85	1.00	1.10	1.38	1.45	1.60	1.85	1.95	2.10	2.45
Bursting Strength	kg/cm ²	ISO 2758	2.16	2.40	2.88	3.36	3.60	4.08	4.32	4.80	5.28	6.00

28 BF PARAMETER

Property	Unit	Method	AdmireCera Corporation									
			90	100	120	140	150	170	180	200	220	250
Grammage	g/m ²	ISO 536	90	100	120	140	150	170	180	200	220	250
Grammage avg.	± 5 %		95-100	95-105	114-126	133-147	143-157	162-178	172-189	190-200	209-231	238-262
Moisture	%	ONLINE	6.5-7.0	6.5-7.0	7.0-7.5	7.0-7.5	7.0-7.5	7.5-8.0	7.5-8.0	8.0-8.5	8.0-8.5	8.0-8.5
Cobb (60sec)	g/m ²	ISO 535	35-40	35-40	40-45	40-45	40-45	40-45	40-45	45-50	45-50	45-50
Bulk	cc/g	ISO 534	1.50-1.60	1.50-1.60	1.45-1.55	1.40-1.45	1.40-1.45	1.40-1.45	1.37-1.45	1.37-1.45	1.37-1.45	1.37-1.45
RCT CD	kn/m	ISO 9895	1.00	1.10	1.15	1.45	1.50	1.75	2.00	2.15	2.25	2.65
Bursting Strength	kg/cm ²	ISO 2758	2.52	2.80	3.36	3.92	4.20	4.76	5.04	5.60	6.16	7.00

35 BF PARAMETER

Property	Unit	Method	AdmireCera Corporation									
			90	100	120	140	150	170	180	200	220	250
Grammage	g/m ²	ISO 536	90	100	120	140	150	170	180	200	220	250
Grammage avg.	± 5 %		95-100	95-105	114-126	133-147	143-157	162-178	172-189	190-200	209-231	238-262
Moisture	%	ONLINE	6.5-7.0	6.5-7.0	7.0-7.5	7.0-7.5	7.0-7.5	7.5-8.0	7.5-8.0	8.0-8.5	8.0-8.5	8.0-8.5
Cobb (60sec)	g/m ²	ISO 535	35-40	35-40	40-45	40-45	40-45	40-45	40-45	45-50	45-50	45-50
Bulk	cc/g	ISO 534	1.50-1.60	1.50-1.60	1.45-1.55	1.40-1.45	1.40-1.45	1.40-1.45	1.37-1.45	1.37-1.45	1.37-1.45	1.37-1.45
RCT CD	kn/m	ISO 9895	1.15	1.25	1.30	1.55	1.65	1.95	2.20	2.35	2.48	3.00
Bursting Strength	kg/cm ²	ISO 2758	3.15	3.50	4.20	4.90	5.25	5.95	6.30	7.00	7.70	8.75